

Tenax[®] DRY REINFORCEMENTS

Preliminary Product Data Sheet

Brand name	Tenax™	
Product type	DRNF	
	Dry Reinforcement Non-Crimp Fabric	
Product key	710091 X01 (70468)	
Product designation	DRNF IM BA 0380 710091 X01	
Variant	X01: PB1_10-V6_04-IMS65- BA11-Y6_TL36-0380	
Construction	V/0°/V/90°/PB	

Detail construction

Layer		Fiber	Areal weight [g/m ²]
Stitch	Loop-side		
5	Powder binder		10
4	90°	Tenax [™] -E IMS65 E23 24K 830tex	190
3	Veil		4
2	0°	Tenax [™] -E IMS65 E23 24K 830tex	190
1	Veil		4
Stitch	Tricot-loop		

+ 4 g for stitching yarn

380 g/m²	
402 g/m ²	
1270 mm or 2540 mm	
3.6 mm	
1400/2800 mm x 152.4 mm x 10 mm	
50 m - 100 m	

Process parameter

Product features

- If veil based toughening technology is part of the product:
 It is developed for all resin infusion processes with curing temperature of approx. 180 °C.
- If powder binder is part of the product: The preform recommendation is to apply vacuum on preform package and hold for 20 min. at 120 °C.
 - All data shown are typical values representative of the material and cannot be guaranteed. Properties may vary depending on samples preparation and test methods.
 - For each shipment an inspection certificate is generated and supplied.
 - A detailed customer specification is arranged on request.
 - The export or transfer of carbon fiber products can be subject to authorization, depending on end-use and final destination.

customer@teijin.co.jp sales@teijincarbon.com info@teijincarbon.us