

Brand name	Tenax™
Product type	DRWF Dry Reinforcement Woven Fabric
Product key	720008 X01
Product designation	DRWF IM UD 0268 720008 X01
Variant	X01: PB3_2_03-IMS65- UD-Y5_RP11-0268



Detail construction

Layer	Fiber	Areal weight [g/m ²]
3	Powder binder	3
2	Warp (0°)	Tenax™-E IMS65 E23 24K 830tex
	Weft (90°)	Combi-fusible bonding yarn
1	Powder binder	3

Product features

Carbon fiber areal weight incl. sizing	268 g/m ²
Total areal weight	276 g/m ²
Fabric width	1250 mm
Weave	Plain weave
Paper core dimension	1400 mm x 152.4 mm x 10 mm
Typical roll length	50 m - 100 m

Process parameter

- If veil based toughening technology is part of the product:
It is developed for all resin infusion processes with curing temperature of approx. 180 °C.
- If powder binder is part of the product:
The preform recommendation is to apply vacuum on preform package and hold for 20 min. at 120 °C.

- All data shown are typical values representative of the material and cannot be guaranteed. Properties may vary depending on samples preparation and test methods.
- For each shipment an inspection certificate is generated and supplied.
- A detailed customer specification is arranged on request.
- The export or transfer of carbon fiber products can be subject to authorization, depending on end-use and final destination.